


COMET Oxy/Acetylene Welding Tips



Type 551 specifications

Part No.	Model No.	Tip size	Steel thickness	Pressure kPa oxygen	Pressure kPa acetylene	Consumption each gas
307056	551	4	0.9mm	50	50	1.5 l/min
307057	551	6	1.2mm	50	50	1.5 l/min
307000	551	8	2.0mm	50	50	2.0 l/min
307001	551	10	2.6mm	50	50	3.0 l/min
307002	551	12	3.2-4.0mm	50	50	4.0 l/min
307003	551	15	5.0-6.5mm	50	50	6.5 l/min
307004	551	20	8.2-10.0mm	50	50	12.0 l/min
307005	551	26	13-19mm	50	50	22.0 l/min
307006	551	32	25mm	100	100	38.0 l/min
307026	551	8-32	2.0-25mm	-	-	-

COMET Oxy/LP Gas Brazing Tips



Type 554 specifications

Part No.	Model No.	Tip size	Steel thickness	Pressure kPa oxygen	Pressure kPa LP Gas
307068	554	8	2.0mm	50	50
307059	554	15	5.0-6.5mm	50	50